

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **2000178361 A**

(43) Date of publication of application: **27.06.2000**

(51) Int. Cl **C08J 3/22**

C08K 5/098, C08K 5/134, C08K 5/20, C08K 5/3415, C08K 5/3477,
C08K 5/378, C08K 13/02, C08L 23/02, C08L 23/06, C08L 23/08,
C08L 23/12, C08L 23/20

(21) Application number: **10355202**

(22) Date of filing: **14.12.1998**

(71) Applicant: **DAINICHISEIKA COLOR & CHEM
MFG CO LTD**

(72) Inventor: **OSHIMA KOTARO
NODA MITSUO**

(54) RESIN MASTERBATCH FOR COLORING

(57) Abstract:

PROBLEM TO BE SOLVED: To stably produce a high-quality colored polyolefin film without allowing resinous deposits to appear in a process for producing the same from a mixture comprising a diluting resin and a color masterbatch by using a color masterbatch prepared by using a polyolefin resin having the same quality as that of the diluting resin,

SOLUTION: This masterbatch is for coloring a 5-200 μm -thick polyolefin film and is prepared by using a polyolefin resin having the same quality as that of a diluting resin for producing the film. Preferably, the masterbatch comprises 30-99.95 wt.% polyolefin resin, 0.01-60 wt.% pigment, 0.01-60 wt.% polyethylene wax, 0.01-5 wt.% metal soap, and 0.01-3 wt.% phenolic antioxidant. The wt, average mol.wt. of the polyolefin resin is preferably 20,000 or higher, The polyethylene wax is preferably a low-molecular weight polyethylene having a number average mol.wt. of 300-8,000.

COPYRIGHT: (C)2000,JPO